



## TECHNICAL DATA SHEET

version 09.2008

*LithoFoam NWF S* page 1/1

### 1. Product Specification

Trade Name: **LithoFoam NWF S**

Product Description: **LithoFoam NWF S** is solely developed for the joint use of LithoFoam protein based foaming agents for the manufacturing of LithoPore foamed concrete. **LithoFoam NWF S** is curing the LithoFoam proteins and forming a strong interlink between the protein molecules through metal ions. As a result the compressive strength of the manufactured foamed concrete LithoPore can be increased on average by 30 %. For this reason **LithoFoam NWF S** is especially suitable for the cast in situ application of foamed concrete. Alternatively the cement quantity can be reduced by 30 % on average to save costs without reducing the compressive strength.

### 2. Physical Data

Composition:	light blue liquid
Density:	1.20 – 1.35 g/ml
pH-Value (original):	2.25-3.25
pH-Value (10 g/l):	3.50-4.50
pH-Value (1 g/l):	5.25-6.25
Electrolytical conductivity (original):	27-31 mS/cm
Electrolytical conductivity (10 g/l):	1.9-2.3 mS/cm
Electrolytical conductivity (1 g/l):	0.6-0.9 mS/cm

### 3. Active Agents Content

Average value 5-8 %

### 4. Special Properties

**LithoFoam NWF S** is frost-resistant.

### 5. General Information, Application

**LithoFoam NWF S** has to be dosage always in relation to the cement quantity.

Dosage range: 1.50-2.50 % per cement  
Recommended dosage: 2.00 % per cement

The optimum effect and dosage depends on the cement quality and shall be tested out by the end user.

**LithoFoam NWF S** is recommended to be used for cast in situ wall fillings. The product is stabilizing the foamed concrete up to a wall height of 3 meters and is avoiding any sedimentation.

The information contained in this product specification is based on our current state of knowledge and experience. It does not free the user from making his own tests and trial applications. A legally binding assurance of certain properties cannot be inferred from this information. Any existing patent rights as well as any pertinent legal regulations must be observed by the recipient of our products under his own responsibility.



Dr. Lucà & Partner Ingenieurkontor GmbH  
Krottnaurerstr. 26 • D-14129 Berlin • Germany

Telephone: +49 (0)30 457989680 • Telefax: +49 (0)30 457989689 • Email: info@dr-luca.com • Internet: http://www.dr-luca.com

Managing Director: Dr. rer. oec. Marcello H. M. Lucà

HR 45942 Amtsgericht Berlin Charlottenburg • Ust.-Ident.-Nr.: DE155530778 • Steuer-Nr. 29/507/03677

Bankers: Landes Bank Berlin, Germany • Bank key (BLZ): 100 500 00 • Acc. (Kto.-Nr.): 66 0700 1473

IBAN: DE3410050000 6607001473 • SWIFT-BIC.: BELADEBEXXX